

technical information

# **Surface Treatment / Care Products Product Information** Junckers PRO SEAL

### **General Description**

Junckers PRO SEAL is a primer designed for professional use in combination with Junckers High Performance Commercial or Junckers HP SPORT.

Compared to similar products Junckers PRO SEAL contains solvents with milder odour and solvency power.

**Technical Data** 

**Product:** Air-drying alkyd in low odour solvents.

Package sizes: 2.5, 5 and 10 litres.

Appearance: Provides wood with a deep, warm glow.

Coverage: 10 m<sup>2</sup> per litre.

**Application tools:** Brush, mohair roller, air/airless spray.

**Substrate temperature:** Minimum 10°C.

Dilution: Junckers PRO SEAL is delivered ready for use.

**Drying time:** Sanding and recoating: 24 hours at 23°C, 50 %RH.

Allow to dry thoroughly prior to overcoating.

Cleaning of tools: Junckers Thinner 007.

Storage: Lasts for 2 years if unopened and stored at 20°C.

Once opened the product will start to form a skin and may harden in

the can.



**System Recommendations** 

High traffic areas: 1 coat Junckers PRO SEAL 10 m<sup>2</sup>/ltr.

+ 2 coats Junckers High Performance Commercial 10 m<sup>2</sup>/ltr.

Low traffic areas: 1 coat **Junckers PRO SEAL** 10 m<sup>2</sup>/ltr.

+ 1-2 coat **Junckers PRO TECH** 10 m<sup>2</sup>/ltr.

Sport: 1 coat **Junckers PRO SEAL** 10 m<sup>2</sup>/ltr.

+ 2 coats Junckers HP SPORT 10 m<sup>2</sup>/ltr.

### **Directions for Use**

#### **Untreated/sanded floors:**

Ensure that the surface is absolutely clean, dry and free from dust, wax, grease, polish etc. Sand away wax, oil stains, lacquer residue etc.

Vacuum sanding dust. Apply Junckers PRO SEAL and allow to dry.

Sand with fine paper grain 150-180 longitudinally to the fibres of the wood before applying further coats according to above "System Recommendations".

#### Previously lacquered floors:

Machine sand before lacquering with Junckers PRO SEAL. Use grain size 24-36 to strip old coats. Then remove abrasion marks with grain size 60-80. Finally, use grain size 100-120 to obtain a completely smooth surface. Vacuum sanding dust and wipe with a well wrung cloth and clean water. Then seal the floor as described under "Untreated/Sanded floors".

#### **Important!**

Before use of the product, read the label on the container carefully and observe the advised precautionary safety measures

#### Important!

Stir well before use.

## **Further information**

#### Products:

F 6.2 - Junckers PRO TECH

F 7.5 - Junckers Thinner 007

F 8.2 - Junckers HP Sport

F 8.5 - Junckers High Performance Commercial

www.junckers.com

Junckers Ltd.